



# THE OPTIMIZATION AND MATHEMATICAL MODELLING – THE PRECONDITION FOR INCREASING OF RECOVERIES FROM DOMESTIC MINES

Boris KRSTEV<sup>2</sup>, Aleksandar KRSTEV<sup>1</sup>, Mirjana GOLOMEOVA<sup>2</sup>, Afrodita ZENDELSKA<sup>2</sup>, Zivko GOCEV<sup>3</sup>

<sup>1</sup>Goce Delcev University, Faculty of Computer Sciences, 2000 Stip, The Republic of Macedonia,  
[aleksandar.krstev@ugd.edu.mk](mailto:aleksandar.krstev@ugd.edu.mk)

<sup>2</sup>Goce Delcev University, Faculty of Natural & Technical Sciences, 2000 Stip, The Republic of Macedonia, [boris.krstev@ugd.edu.mk](mailto:boris.krstev@ugd.edu.mk)

<sup>3</sup>Bucim Mine, 2000 Radovis, The Republic of Macedonia, [gocevz@yahoo.com](mailto:gocevz@yahoo.com)

<sup>2</sup>Goce Delcev University, Faculty of Natural & Technical Sciences, 2000 Stip, The Republic of Macedonia, [mirjana.golomeova@ugd.edu.mk](mailto:mirjana.golomeova@ugd.edu.mk)

## ABSTRACT

*The increasing in the chalcopyrite copper Bucim mine are gone forward to renewed reagent regime, including and involving new reagents for increased recovery of copper and gold. The optimization and mathematical linear are good example for improvement of industrial recoveries in flotation circuit. Nevertheless, the choice between flotation and new leaching or bioleaching method are challenge for future.*

*The optimization techniques, formating the mathematical model and adequate model for carried out investigations, by means of tables and figures will show the optimal quantity in reagent regime (collectors), particle size, flotation time, rougher flotation, conditioning time etc.*

## KEYWORDS

*Collectors, Flotation time, Optimization, Reagent regime, Particle size.*

## **1.General principles**

The previous carried out laboratory investigations with application of the new collectors CYTEC and frothers confirmed that there is possibility for significantly improvement of the gold recovery with same copper quality and decreasing of the CaO consumption. The investigations with reagents Aerophine 3404, Aero XD 5002 and frother OP-F49 in the previous period (2010) were very short because of the low quality and variations of the ores. Variations of the ore from 0.15-0.22%Cu, instability of the flotation and other problems in the flotation process. The combination of the Aerophine 3404, KEX:KBX= 1:1, NaIPX, SKIK Bz 2000, in the different points of the flotation process gave significantly better results than early. The process was prolonged with pH=10.5 and the point of addition of CaO was at the hydro cyclone (70%) and 30% in the flotation process. The conclusions of these investigations were very heavy for sure confirmation, but the obtained results were close to the previous results by standard conditions (specially for Au), may be better but not significantly. The Au content in the ore was од 0,19-0,29 gr/t, in the concentrate 8-12,3 gr/t, with Au recovery from 45-55% (some appearances up to 60%), but the copper recovery in the standard interval. Considering these investigations in laboratory and industrial real conditions may be concluded that:

- The instability and relative short period of investigations in the real conditions have contributed for obtaining the technological parameters closed to the standard conditions,
- As a result of the good regrinding, it was very heavy to clean the rough concentrate Cu/Au,
- Using higher pH, higher than standard in the rougher flotation (elimination of pyrite flotation) by Aerophine 3404, it will be expected higher quality and content of Cu/Au,
- In the existing real conditions of flotation at pH 11,0-11,6 and consumption of Aerophine 3404 (AP3404) from 18-22 gr/t, together with change of adaptive changeable reagent regime by different collectors (the combination from Aerophine 3404, KEX:KBX, NaIPX),
- The prolonged changes of the reagent regime with contemporary addition of new reagents (Bz 2000 = 4-8 gr/t + KEX:KBX=1:1 = 8-4 gr/t, total 12 gr/t) in the grinding cycle, together with addition of NaIPX in the conditiooner with 8-10 gr/t, in the flotation process (rougher and controlled flotation) with 2-4 gr/t, or total addition of 14 gr/t NaIPX,

The tests R1-R6 are related to the ore grindibility in the presence of the BZ2000 (7 gr/t), conditioning time (6 min.) with BZ2000 (5 gr/t) + DowF (10 gr/t) after 4 min., rougher flotation (4 min.), and scavenging flotation (4+4 minutes) (NaIPX 6+4 gr/t + DowF 5+5 gr/t). The tests R7-R10 are related for the ore grinding in the presence of the KEX:KBX= 8 gr/t, conditioning time of (6 min.) with BZ2000 (4 gr/t) + DowF (10 gr/t) after 4 minutes, rougher flotation (4 min.), and scavenging flotation (4+4 minutes) (NaIPX 8+4 gr/t + DowF 5+5 gr/t). The tests R11-R18 are related for the grinding ore in the presence of KEX:KBX= 6 gr/t, conditioning time of (6 min.) with KEX:KBX= (4 gr/t) + DowF (10 gr/t) after 4 minutes, rougher

flotation (4 min.), and scavenging flotation (4+4 minutes) (NaIPX 8+4 gr/t + DowF 5+5 gr/t), and variants with condition 6 minutes with BZ2000 (4 gr/t) + dispersgator (50 gr/t), or variant with BZ2000 in all existing phases: conditioning, rougher and control flotation. The tests R19-R26 are related for grinding ore in the presence of BZ2000 = 7 gr/t, conditioning time (6 minutes) with BZ2000 (5 gr/t) + DowF (10 gr/t) after 4 minutes, rougher flotation (4 minutes), and control flotation (4+4 minutes) (NaIPX 6+6 gr/t + DowF 5+5 gr/t), with variants with conditioning (6 minutes) with BZ2000 (4 gr/t) + dispersgator (100 and 150 gr/t), or variant with BZ2000 in all existing phases: conditioning, rougher and control flotation.

*Table 1. Investigated conditions for flotation for copper - plan experiments (DOE)*

Test	Collectors, type	Collector, gr/t	pH	-200#, %	Time, min.
R-1	<b>BZ 2000+BZ2000+NaIPX</b>	22	11.75	42.90	15
R-2	<b>BZ 2000+BZ2000+NaIPX</b>	22	11.75	44.90	15
R-3	<b>BZ 2000+BZ2000+NaIPX</b>	22	11.75	48.10	18
R-4	<b>BZ 2000+BZ2000+NaIPX</b>	22	11.75	49.10	18
R-5	<b>BZ 2000+BZ2000+NaIPX</b>	22	11.75	54.30	21
R-6	<b>BZ 2000+BZ2000+NaIPX</b>	22	11.75	55.60	21
R-7	<b>KEX:KBX + BZ2025+NaIPX</b>	24	11.80	50.00	
R-8	<b>KEX:KBX + BZ2025+NaIPX</b>	24	11.80	50.00	
R-9	<b>KEX:KBX + BZ2025+NaIPX</b>	24	11.80	50.00	
R-10	<b>KEX:KBX + BZ2025+NaIPX</b>	24	11.80	50.00	
R-11	<b>KEX:KBX +KEX:KBX+NaIPX</b>	22	11.80		
R-12	<b>KEX:KBX +KEX:KBX+NaIPX</b>	22	11.80		
R-13	<b>KEX:KBX +KEX:KBX+NaIPX</b>	22	11.80		
R-14	<b>KEX:KBX +KEX:KBX+NaIPX</b>	22	11.80		
R-15	<b>BZ 2000+BZ2000+NaIPX</b>	22	11.80		
R-16	<b>BZ 2000+BZ2000+NaIPX</b>	22	11.80		
R-17	<b>BZ 2000+BZ2000+BZ2000</b>	22	11.80		
R-18	<b>BZ 2000+BZ2000+BZ2000</b>	22	11.80		
R-19	<b>BZ 2000+BZ2000+NaIPX</b>	24	11.75		d – dispersgator 100gr/t
R-20	<b>BZ 2000+BZ2000+NaIPX</b>	24	11.75		
R-21	<b>BZ 2000+BZ2000+NaIPX+d</b>	24	11.75		
R-22	<b>BZ 2000+BZ2000+NaIPX+d</b>	24	11.75		
R-23	<b>BZ 2000+BZ2000+NaIPX</b>	20	11.75		d – dispersgator 150gr/t
R-24	<b>BZ 2000+BZ2000+NaIPX</b>	20	11.75		
R-25	<b>BZ 2000+BZ2000+NaIPX+d</b>	20	11.75		
R-26	<b>BZ 2000+BZ2000+NaIPX+d</b>	20	11.75		

Table 2. Tests with a plan experiments on copper

Tests	Content, Cu%			Recovery, Cu%	
	r	k	j	K	J
R-1	0.190	<b>2.40</b>	0.038	<b>81.29</b>	18.71
R-2	0.175	<b>3.42</b>	0.043	<b>76.42</b>	23.58
R-3	0.186	<b>2.16</b>	0.034	<b>83.34</b>	16.66
R-4	0.194	<b>2.22</b>	0.027	<b>87.12</b>	12.88
R-5	0.211	<b>3.38</b>	0.022	<b>90.14</b>	9.86
R-6	0.237	<b>3.82</b>	0.024	<b>90.45</b>	9.55
R-7	0.249	<b>4.00</b>	0.031	<b>88.25</b>	11.75
R-8	0.251	<b>6.40</b>	0.031	<b>88.06</b>	11.94
R-9	0.250	<b>4.60</b>	0.031	<b>88.21</b>	11.79
R-10	0.247	<b>4.82</b>	0.029	<b>88.79</b>	11.21
R-11	0.282	<b>8.60</b>	0.077	<b>73.31</b>	26.69
R-12	0.308	<b>8.40</b>	0.075	<b>76.34</b>	23.66
R-13	0.292	<b>8.00</b>	0.070	<b>76.70</b>	23.30
R-14	0.290	<b>8.40</b>	0.069	<b>76.82</b>	23.18
R-15	0.297	<b>7.60</b>	0.075	<b>75.49</b>	24.51
R-16	0.301	<b>8.40</b>	0.072	<b>76.74</b>	23.26
R-17	0.301	<b>5.40</b>	0.083	<b>73.56</b>	26.44
R-18	0.297	<b>8.20</b>	0.082	<b>73.13</b>	26.87
R-19	0.180	<b>3.40</b>	0.025	<b>86.77</b>	13.23
R-20	0.178	<b>3.46</b>	0.023	<b>87.67</b>	12.33
R-21	0.187	<b>4.88</b>	0.023	<b>88.14</b>	11.86
R-22	0.187	<b>4.22</b>	0.025	<b>87.14</b>	12.86
R-23	0.184	<b>2.10</b>	0.031	<b>84.41</b>	15.59
R-24	0.196	<b>3.30</b>	0.030	<b>85.44</b>	14.56
R-25	0.194	<b>3.52</b>	0.032	<b>84.27</b>	15.73
R-26	0.203	<b>3.64</b>	0.033	<b>84.54</b>	15.46

Table 3. Investigated conditions for flotation for gold - plan

Tests	Collectors, typ	Coll.,gr/t	pH
A-1	<b>BZ 2000+Naskol+NaIPX</b>	22	11.75
A-2	<b>BZ 2000+Naskol+NaIPX</b>	22	11.75
A-3	<b>KEX:KBX +NaIPX</b>	18	11.75
A-4	<b>KEX:KBX + NaIPX</b>	18	11.75
A-5	<b>KEX:KBX +NaIPX</b>	22	11.80
A-6	<b>KEX:KBX + NaIPX</b>	22	11.80
A-7	<b>KEX:KBX+BZ 2000 +NaIPX</b>	22	11.80
A-8	<b>KEX:KBX+BZ 2000 + NaIPX</b>	22	11.80
A-9	<b>Naskol+NaIPX</b>	22	10.60
A-10	<b>Naskol+NaIPX</b>	22	10.60
A-11	<b>KEX:KBX + Naskol</b>	22	11.80
A-12	<b>KEX:KBX + Naskol</b>	22	11.80
A-13	<b>KEX:KBX + NaIPX</b>	16	11.80
A-14	<b>KEX:KBX + NaIPX</b>	16	11.80
A-15	<b>KAX + NaIPX</b>	22	11.80
A-16	<b>KAX + + Naskol + NaIPX</b>	22	11.80

The group of tests (R1÷R-6), (R7÷R-10), (R11÷R-18) and (R19÷R-26) are carried out in the laboratory conditions showing the satisfactory results with increasing of the grinding time, but other results are at the level of the industrial obtained result (application of the different collectors and combination of the different types of collectors at the standard pH value). The tests A1-A16 are carried out in the different conditions and different reagent regime and collectors, conditioning, rougher and control flotation with the reagent regime shown at the tables.

*Table 4. Tests with a plan experiments on gold*

Tests	Content, (k ,r, j), Au(gr/t)	Recovery (K,J), Au(gr/t)		
A-1	<b>5.700</b>	0.281	0.170	<b>40.63</b>
A-2	<b>4.200</b>	0.279	0.170	<b>40.67</b>
A-3	<b>4.800</b>	0.278	0.160	<b>43.98</b>
A-4	<b>5.200</b>	0.264	0.150	<b>44.38</b>
A-5	<b>5.500</b>	0.320	0.110	<b>66.99</b>
A-6	<b>5.800</b>	0.390	0.120	<b>70.68</b>
A-7	<b>4.300</b>	0.308	0.100	<b>69.13</b>
A-8	<b>4.200</b>	0.261	0.090	<b>66.89</b>
A-9	<b>4.000</b>	0.303	0.100	<b>68.69</b>
A-10	<b>4.000</b>	0.339	0.120	<b>66.62</b>
A-11	<b>3.600</b>	0.269	0.110	<b>60.94</b>
A-12	<b>4.200</b>	0.272	0.110	<b>61.09</b>
A-13	<b>4.900</b>	0.335	0.120	<b>65.80</b>
A-14	<b>5.100</b>	0.391	0.130	<b>68.49</b>
A-15	<b>3.400</b>	0.165	0.025	<b>85.48</b>
A-16	<b>3.700</b>	0.242	0.050	<b>80.39</b>

*Table 5. Investigated conditions for flotation - plan experiments (DOE) 2011/12*

Tests	Collectors, type	Collector, gr/t	pH	Froth type	Froth, gr/t
T – 1	<b>BZ+KEX+KBX+NaIPX</b>	22	11.8	<b>DowF</b>	20
T - 2	<b>BZ+KEX+KBX+NaIPX</b>	22	11.8	<b>OP 549</b>	20
O'-1	<b>Aerophine (3404+5002) (1:1) 50%</b>	16	11.0	<b>DowF</b>	20
O'-2	<b>Aerophine (3404+5002) (1:1) 50%</b>	16	10.0		
O'-3	<b>Aerophine (3404+5002) (1:1) 50%</b>	18	11.0		
O'-4	<b>Aerophine (3404+5002) (1:1) 50%</b>	18	10.0		
O'-5	<b>Aerophine (3404+5002) (1:1) 50%</b>	20	11.0		
O'-6	<b>Aerophine (3404+5002) (1:1) 50%</b>	20	10.0		
O'-7	<b>Aerophine (3404+5002) (1:1) 50%</b>	22	11.0		
O'-8	<b>Aerophine (3404+5002) (1:1) 50%</b>	22	10.0		
O'-9	<b>Aerophine (3404+5002) (1:1) 50%</b>	16	10.5		
O'-10	<b>Aerophine (3404+5002) (1:1) 50%</b>	22	10.5		

Table 6. Standard conditions for flotation in Bucim mine

Tests	Collectors, type	Collector, gr/t	pH	Froth type	Froth, gr/t
T - 1	<b>BZ+KEX+KBX+NaIPX</b>	22	11.8	<b>DowF</b>	20
T - 2	<b>BZ+KEX+KBX+NaIPX</b>	22	11.8	<b>OP 549</b>	20

Table 7. Investigated conditions for flotation - plan experiments (DOE) 2011/12

Tests	Collectors, type	Collectors, gr/t	pH	Froth type	Froth, gr/t
T - 1	<b>BZ+KEX+KBX+NaIPX</b>	22	11.8	<b>DowF</b>	20
T - 2	<b>BZ+KEX+KBX+NaIPX</b>	22	11.8	<b>OP 549</b>	20
O-1	<b>Aerophine 3404 (70%)</b>	16	10.5	<b>DowF</b>	20
O-2	<b>Aerophine 3404 (70%)</b>	16	9.5		
O-3	<b>Aerophine 3404 (70%)</b>	18	10.5		
O-4	<b>Aerophine 3404 (70%)</b>	18	9.5		
O-5	<b>Aerophine 3404 (70%)</b>	20	10.5		
O-6	<b>Aerophine 3404 (70%)</b>	20	9.5		
O-7	<b>Aerophine 3404 (70%)</b>	22	10.5		
O-8	<b>Aerophine 3404 (70%)</b>	22	9.5		
O-9	<b>Aerophine 3404 (70%)</b>	20	11.5		
O-10	<b>Aerophine 3404 (70%)</b>	22	11.5		

Table 8. Tests with a plan experiments on copper 2011/12

Tests	Content, Cu%			Recovery, Cu%	
	r	k	j	K	J
T - 1	0.29	2.3	0.053	83.4	16.6
T - 2	0.31	2.8	0.050	85.6	14.4
O-1	0.21	20.54	0.025	<b>88.20</b>	11.80
O-2	0.20	20.68	0.025	<b>87.60</b>	12.40
O-3	0.19	20.85	0.024	<b>87.46</b>	12.54
O-4	0.20	20.98	0.022	<b>89.09</b>	10.91
O-5	0.22	20.77	0.019	<b>91.45</b>	8.55
O-6	0.21	20.90	0.020	<b>90.56</b>	9.44
O-7	0.20	21.21	0.020	<b>90.08</b>	9.92
O-8	0.22	21.44	0.017	<b>92.34</b>	7.66
O-9	0.23	21.10	0.017	<b>92.68</b>	7.32
O-10	0.22	20.46	0.017	<b>92.39</b>	7.61

*Table 9. Tests with a plan experiments on gold 2011/12*

Tests	Content, (k ,r), Au (ppm)		Recovery (K,J), Au (%)	
T - 1	1.40	0.26	56.1	43.9
T - 2	1.49	0.29	49.8	50.2
O-1	2.20	0.22	<b>38.83</b>	61.17
O-2	2.45	0.24	<b>44.20</b>	55.80
O-3	1.95	0.23	<b>46.60</b>	53.40
O-4	2.50	0.19	<b>33.46</b>	66.54
O-5	2.80	0.18	<b>40.07</b>	59.93
O-6	2.25	0.20	<b>34.60</b>	65.40
O-7	1.90	0.23	<b>51.05</b>	48.95
O-8	2.45	0.20	<b>42.06</b>	57.94
O-9	1.95	0.19	<b>36.54</b>	63.46
O-10	2.75	0.21	<b>35.11</b>	64.89

*Table 10. Tests with a plan experiments on copper 2011/12*

Tests	Content, Cu%			Recovery, Cu%	
	r	k	j	K	J
T - 1	0.29	2.3	0.053	83.4	16.6
T - 2	0.31	2.8	0.050	85.6	14.4
O'-1	0.22	20.55	0.021	<b>90.55</b>	9.45
O'-2	0.22	21.25	0.020	<b>89.72</b>	10.28
O'-3	0.23	20.70	0.018	<b>92.25</b>	7.75
O'-4	0.22	21.30	0.020	<b>90.99</b>	9.01
O'-5	0.20	21.70	0.023	<b>88.59</b>	11.41
O'-6	0.23	20.40	0.024	<b>89.66</b>	10.34
O'-7	0.22	20.75	0.018	<b>91.90</b>	8.10
O'-8	0.22	20.55	0.021	<b>90.54</b>	9.46
O'-9	0.21	22.80	0.020	<b>90.55</b>	9.45
O'-10	0.21	22.50	0.018	<b>91.73</b>	8.27

*Table 11. Tests with a plan experiments on gold 2011/12*

Tests	Content, (k ,r), Au (ppm)		Recovery (K,J), Au (%)	
T - 1	1.40	0.26	56.1	43.9
T - 2	1.49	0.29	49.8	50.2
O'-1	1.56	0.19	<b>39.91</b>	60.09
O'-2	1.49	0.25	<b>58.52</b>	41.48
O'-3	1.47	0.22	<b>48.58</b>	51.42
O'-4	1.49	0.23	<b>52.03</b>	47.97
O'-5	1.55	0.24	<b>52.13</b>	47.87
O'-6	1.78	0.20	<b>40.33</b>	59.67
O'-7	2.55	0.17	<b>30.86</b>	69.14
O'-8	2.15	0.19	<b>39.01</b>	60.99
O'-9	2.15	0.20	<b>31.77</b>	68.23
O'-10	1.95	0.19	<b>33.82</b>	66.18

### **3.Results and discussion**

According to the previous investigations and obtained results from these investigations and tests for the Bucim mine ores, these particular investigation are carried out by means of experiment plans, laboratory investigations etc. These investigations show advanced approach for eventual optimization of the flotation process from useful raw material or chalcopyrite ores with possibility of obtaining the optimal results.

### **CONCLUSION**

In this paper is shown practical applicative optimization techniques with formatting the model for adequate reagent regime for carried out investigations. Obtained tabular results will show the optimal quantity in reagent regime (collectors), particle size, flotation time for rougher flotation, conditioning time, some addition of special reagents etc.

### **REFERENCES**

- [1] Mular, A. L., (1980). "Empirical modeling and aptinisation of mineral processes", Mineral Science and Engineering, 4, No 3. Pp 30-42.
- [2] Napier-Munn, T. J., Morrell, S., Morrison, R. D., and Kojovic, T., (1996). 'Mineral comminution circuits: their operation and optimization ". JKMRC., pp. 413.
- [3] Plitt, L. R., (December, 1976). "A mathematical model of the hydrocyclone classifier", *CIM Bull.* 69, 114.
- [4] Povarov A. I., (1978). "Gridrocikloni na obogatitel'nyh fabrikah", "Nedra". Moskva, Russia.
- [5] Renner, V. G., and Cohen, H. E., (June, 1978). "Measurement and interpretation of size distribution of particles within a hydrocyclone", *Trans. IMM.*, Sec. C, 87,139.
- [6] Rowland C. A., (1986). "Ball Mill Scale-up-Diameter Factors., Advances in Mineral Processing", P. Somasundaran Editor Society of Mining Engineers/AIME, 34, 605.
- [7] Svarovsky, L., (1984). "Hydrocyclones", Holt, Rinehart & Winston Ltd, Eastbourne.
- [8] Wiegel R. L., and Li K. A., (1986). "Random Model for Mineral Liberation by Size Reduction", *Trans. AIME*, 238, 179.
- [9] Wills, B. A. (1988). "Mineral Processing Technology", 4<sup>th</sup> edition
- [10] A.Krstev,(2012), PhD Thesis, 2012 UGD-Stip, Macedonia