



**IMPS  
2014**

**14<sup>th</sup> INTERNATIONAL  
MINERAL PROCESSING  
SYMPOSIUM & EXHIBITION**

October 15 - 17, 2014, Pine Bay Hotel, Kuşadası - Turkey



# **PROCEEDINGS OF 14<sup>th</sup> INTERNATIONAL MINERAL PROCESSING SYMPOSIUM**

October 15 - 17, 2014

Kuşadası – Turkey

*Mineral Processing in Everything!*

**Editors**

Üner İPEKOĞLU, Vedat ARSLAN and Sezai ŞEN

*Dokuz Eylül University, Department of Mining Engineering*



*Turkish Mining Development Foundation*

Kuşadası - Turkey

October 15 - 17, 2014

---

Website: [www.imps2014.org](http://www.imps2014.org)

The proceedings are also available in USB flash memory.

Publisher : Turkish Mining Development Foundation  
ISBN : 978-975-441-436-3  
Edited by : Üner İPEKOĞLU, Vedat ARSLAN, Sezai ŞEN  
Printing Layout : Sezai ŞEN, Baran TUFAN  
Published by : Üç Adım Matbaa-Reklam Ltd. Şti. İzmir/Turkey

*The Proceedings of 14<sup>th</sup> International Mineral Symposium was printed by the contribution of TUBITAK.*

## ORGANIZING COMMITTEE

### *Symposium Presidents*

|                    |   |
|--------------------|---|
| Dr. Nevzat KAVAKLI | Deputy Undersecretary, Ministry of Energy & Natural Resources |
| Mustafa AKTAŞ      | General Director of The Turkish Coal Enterprises              |

### *Symposium Chair*

|                         |                        |
|-------------------------|------------------------|
| Prof. Dr. Üner İPEKOĞLU | Dokuz Eylül University |
|-------------------------|------------------------|

### *Institutional Advisory Committee (in alphabetical order)*

|                           |  |
|---------------------------|--|
| Ayhan YÜKSEL              | President, Chamber of Mining Engineers of Turkey |
| Burhan İNAN               | G. Director of The Turkish Hard Coal Enterprises |
| Prof. Dr. Ercüment YALÇIN | Dean, Faculty of Eng., Dokuz Eylül University    |
| Prof. Dr. Güven ÖNAL      | President, Turkish Mining Development Foundation |
| Prof. Dr. Mehmet FÜZÜN    | Rector, Dokuz Eylül University                   |
| Mehmet Hamdi YILDIRIM     | G. Director of The Mining Affairs                |
| M. Ümit AKDUR             | Turkish Gold Miners Association                  |
| Mehmet ÜZER               | G. Director, Mineral Res. & Expl.                |
| Dr. Orhan YILMAZ          | General Manager, Eti Mine Works                  |
| Prof. Dr. Turan BATAR     | President, Mineral Processing Society of Turkey  |

### *Industrial Advisory Committee (in alphabetical order)*

|                      |  |
|----------------------|--|
| Ahmet TEZCAN         | Eti Copper Inc.                            |
| Alp GÜRKAN           | Soma Coal Inc.                             |
| Arif KURTEL          | İmbat Mining Inc                           |
| Bülent TÜFEKÇİOĞLU   | Tüfekçioğlu Rubber, Mac. and Min. Ind. Co. |
| David A. BICKFORD    | Tüprag Metal Mining Industry & Trade       |
| Ergun TUNCER         | Bilfer Mining Inc.                         |
| İsmet SİVRİOĞLU      | Koza Gold Operations Company               |
| Jeremy SHORT         | Anagold Mining Inc.                        |
| Murat Zekeriya AYDIN | Kolin Construction                         |
| Oktay Rifat KUŞOĞLU  | Coal Enterprises Inc.                      |
| Özlem ÖNAL           | Dedeman Mining                             |
| Sabri KARAHAN        | DAMA Engineering Co.                       |
| Savaş ŞAHİN          | Demir Export Inc.                          |
| Serdar NİŞLİ         | Aksa Enerji                                |
| Şeyda ÇAĞLAYAN       | Türk Maadin Inc.                           |

## STEERING COMMITTEE

Prof. Dr. A. Üner İPEKOĞLU  
Prof. Dr. Hüseyin ÖZDAĞ  
Prof. Dr. Güven ÖNAL  
Prof. Dr. Ümit ATALAY  
Prof. Dr. Gülhan ÖZBAYOĞLU  
Prof. Dr. Özcan GÜLSOY  
Prof. Dr. Çetin HOŞTEN  
Prof. Dr. Levent ERGÜN  
Prof. Dr. A. İhsan AROL  
Prof. Dr. Volkan BOZKURT  
Prof. Dr. Gündüz ATEŞOK  
Prof. Dr. Neşet ACARKAN

## HONORARY MEMBERS

Prof. Dr. M. Zeki DOĞAN  
Prof. Dr. Ali AKAR  
Dr. H. Avni YAZAN  
Prof. Dr. Yaşar ÇILINGİR  
Prof. Dr. Suna ATAK  
Prof. Dr. Halim DEMİREL  
Prof. Dr. Erdoğan YIĞIT  
Prof. Dr. İrfan BAYRAKTAR  
Prof. Dr. Mevlüt KEMAL  
Prof. Dr. Mehmet CANBAZOĞLU  
Sabri KARAHAN

## LOCAL COMMITTEE (*Dokuz Eylül University*)

Prof. Dr. Vedat ARSLAN  
Prof. Dr. İlknur CÖCEN  
Prof. Dr. Erol KAYA  
Prof. Dr. Mehmet TANRIVERDİ  
Assoc. Prof. Dr. Tayfun ÇİÇEK  
Assoc. Prof. Dr. Abdullah SEYRANKAYA  
Assoc. Prof. Dr. Ufuk MALAYOĞLU  
Assoc. Prof. Dr. Sezai ŞEN  
Assist. Prof. Dr. Hatice YILMAZ  
Lecturer Dr. Özge GÖK  
Lecturer Dr. Baran TUFAN  
Resc. Assist. Dr. Erkan GÜLER  
Resc. Assist. Dr. Gül Akar ŞEN  
Resc. Assist. Dr. Vedat Taylan ENGİN  
Resc. Assist. Ebru TUFAN  
Resc. Assist. Çağrı ÇERİK  
Resc. Assist. Ümit HORASAN

## **THE OPTIMIZATION AND THE PRECONDITION FOR INCREASING OF GOLD RECOVERIES FROM DOMESTIC MINES**

Boris Krstev<sup>1,a</sup> and Aleksandar Krstev<sup>2</sup>

<sup>1</sup>Goce Delcev University, Faculty of Natural & Technical Sciences, 2000 Stip, The Republic of Macedonia

<sup>2</sup>Goce Delcev University, Faculty of Computer Sciences, 2000 Stip, The Republic of Macedonia,

*a. Corresponding author (boris.krstev@ugd.edu.mk)*

### **ABSTRACT**

The increasing in the chalcopyrite copper Bucim mine are gone forward to renewed reagent regime, including and involving new reagents for increased recovery of copper and gold. The optimization and mathematical linear are good example for improvement of industrial recoveries in flotation circuit. Nevertheless, the choice between flotation and new leaching or bioleaching method are challenge for future. The optimization techniques, formatting the mathematical model and adequate model for carried out investigations, by means of tables and figures will show the optimal quantity in reagent regime (collectors), particle size, flotation time, rougher flotation, conditioning time etc.

### **1. General principles**

The previous carried out laboratory investigations with application of the new collectors and frothers confirmed that there is possibility for significantly improvement of the gold recovery with same copper quality and decreasing of the CaO consumption. The investigations with reagents Aerophine 3404, Aero XD 5002 and frother OP-F49 in the previous period (2010/11) were very short because of the low quality and variations of the ores. Variations of the ore from 0.15-0.22%Cu, instability of the flotation and other problems in the flotation process. The combination of the Aerophine 3404, KEX:KBX= 1:1, NaIPX, SKIK- Bz 2000, in the different points of the flotation process gave significantly better results that early. The process was prolonged with pH=10.5 and the point of addition of CaO was at the hydro cyclone (70%) and 30% in the flotation process. The conclusions of these investigations were very heavy for sure confirmation, but the obtained results were close to the previous results by standard conditions (specially for Au), may be better but not significantly. The Au content in the ore was on 0,19-0,29 gr/t, in the concentrate

8-12,3 gr/t, with Au recovery from 45-55% (some appearances up to 60%), but the copper recovery in the standard interval. Considering these investigations in laboratory and industrial real conditions may be concluded that:

- The instability and relative short period of investigations in the real conditions have contributed for obtaining the technological parameters closed to the standard conditions,
- As a result of the good regrinding, it was very heavy to clean the rough concentrate Cu/Au,
- Using higher pH, higher than standard in the rougher flotation (elimination of pyrite flotation) by Aerophine 3404, it will be expected higher quality and content of Cu/Au,
- In the existing real conditions of flotation at pH 11,0-11,6 and consumption of Aerophine 3404

- (AP3404) from 18-22 gr/t, together with change of adaptive changeable reagent regime by different collectors (the combination from Aerophine 3404, KEX:KBX, NaIPX),
- The prolonged changes of the reagent regime with contemporary addition of new reagents (Bz 2000 = 4-8 gr/t + KEX:KBX=1:1 = 8-4 gr/t, total 12 gr/t) in the grinding cycle, together with addition of NaIPX in the conditioner with 8-10 gr/t, in the flotation process (rougher and controlled flotation) with 2-4 gr/t, or total addition of 14 gr/t NaIPX

The tests A1-A16 are related to the ore grindability in the presence of the BZ2000 (7 gr/t), conditioning time (6 min.) with BZ2000 (5 gr/t) + DowF (10 gr/t) after 4 min., rougher flotation (4 min.), and scavenging flotation (4+4 minutes) (NaIPX 6+4 gr/t + DowF 5+5 gr/t). The tests A7-A8 are related for the ore grinding in the presence of the KEX:KBX= 8 gr/t, conditioning time of (6 min.) with BZ2000 (4 gr/t) + DowF (10 gr/t) after 4 minutes, rougher flotation (4 min.), and scavenging flotation (4+4 minutes) (NaIPX 8+4 gr/t + DowF 5+5 gr/t). The tests A11-A16 are related for the grinding ore in the presence of KEX:KBX= 6 gr/t, conditioning time of (6 min.) with KEX:KBX= (4 gr/t) + DowF (10 gr/t) after 4 minutes, rougher flotation (4 min.), and scavenging flotation (4+4 minutes) (NaIPX 8+4 gr/t + DowF 5+5 gr/t). and variants with condition 6 minutes with BZ2000 (4 gr/t) + dispergator (50 gr/t), or variant with BZ2000 in all existing phases: conditioning, rougher and control flotation.

Table 1. Investigated conditions for flotation for gold - plan

| Tests | Collectors, typ       | Coll., gr/t | pH    |
|-------|-----------------------|-------------|-------|
| A-1   | BZ 000+Naskol+NaIPX   | 22          | 11.75 |
| A-2   | BZ 000+Naskol+NaIPX   | 22          | 11.75 |
| A-3   | KEX:KBX +NaIPX        | 18          | 11.75 |
| A-4   | KEX:KBX + NaIPX       | 18          | 11.75 |
| A-5   | KEX:KBX +NaIPX        | 22          | 11.80 |
| A-6   | KEX:KBX + NaIPX       | 22          | 11.80 |
| A-7   | KEX:KBX+BZ 2000+NaIPX | 22          | 11.80 |
| A-8   | KEX:KBX+BZ 2000+NaIPX | 22          | 11.80 |
| A-9   | Naskol+NaIPX          | 22          | 10.60 |
| A-0   | Naskol+NaIPX          | 22          | 10.60 |
| A-11  | KEX:KBX + Naskol      | 22          | 11.80 |
| A-12  | KEX:KBX + Naskol      | 22          | 11.80 |
| A-13  | KEX:KBX + NaIPX       | 16          | 11.80 |
| A-14  | KEX:KBX + NaIPX       | 16          | 11.80 |
| A-15  | KAX + NaIPX           | 22          | 11.80 |
| A-16  | KAX + Naskol + NaIPX  | 22          | 11.80 |

Table 2. Tests with a plan experiments on gold

| Tests | Content, (k, r, j), Au(gr/t) |       |       | Recovery (K, J), Au(gr/t) |       |
|-------|------------------------------|-------|-------|---------------------------|-------|
|       | k                            | r     | j     | K                         | J     |
| A-1   | 5.700                        | 0.281 | 0.170 | 40.63                     | 59.37 |
| A-2   | 4.200                        | 0.279 | 0.170 | 40.67                     | 59.33 |
| A-3   | 4.800                        | 0.278 | 0.160 | 43.98                     | 56.02 |
| A-4   | 5.200                        | 0.264 | 0.150 | 44.38                     | 55.62 |
| A-5   | 5.500                        | 0.320 | 0.110 | 66.99                     | 33.01 |
| A-6   | 5.800                        | 0.390 | 0.120 | 70.68                     | 29.32 |
| A-7   | 4.300                        | 0.308 | 0.100 | 69.13                     | 30.87 |
| A-8   | 4.200                        | 0.261 | 0.090 | 66.89                     | 33.11 |
| A-9   | 4.000                        | 0.303 | 0.100 | 68.69                     | 31.31 |
| A-10  | 4.000                        | 0.339 | 0.120 | 66.62                     | 33.38 |
| A-11  | 3.600                        | 0.269 | 0.110 | 60.94                     | 39.06 |
| A-12  | 4.200                        | 0.272 | 0.110 | 61.09                     | 38.91 |
| A-13  | 4.900                        | 0.335 | 0.120 | 65.80                     | 34.20 |
| A-14  | 5.100                        | 0.391 | 0.130 | 68.49                     | 31.51 |
| A-15  | 3.400                        | 0.165 | 0.025 | 85.48                     | 14.52 |
| A-16  | 3.700                        | 0.242 | 0.050 | 80.39                     | 19.61 |

The tests A1-A16 are carried out in the different conditions and different reagent regime and collectors, conditioning, rougher and control flotation with the reagent regime shown at the tables.

Table 3. Tests with a plan experiments on gold 2012/13

| Tests | Content, (k.r), Au (ppm) |      | Recovery (K,J), Au (%) |       |
|-------|--------------------------|------|------------------------|-------|
| T-1   | 1.40                     | 0.26 | 56.1                   | 43.9  |
| T-2   | 1.49                     | 0.29 | 49.8                   | 50.2  |
| O-1   | 2.20                     | 0.22 | <b>38.83</b>           | 61.17 |
| O-2   | 2.45                     | 0.24 | <b>44.20</b>           | 55.80 |
| O-3   | 1.95                     | 0.23 | <b>46.60</b>           | 53.40 |
| O-4   | 2.50                     | 0.19 | <b>33.46</b>           | 66.54 |
| O-5   | 2.80                     | 0.18 | <b>40.07</b>           | 59.93 |
| O-6   | 2.25                     | 0.20 | <b>34.60</b>           | 65.40 |
| O-7   | 1.90                     | 0.23 | <b>51.05</b>           | 48.95 |
| O-8   | 2.45                     | 0.20 | <b>42.06</b>           | 57.94 |
| O-9   | 1.95                     | 0.19 | <b>36.54</b>           | 63.46 |
| O-10  | 2.75                     | 0.21 | <b>35.11</b>           | 64.89 |

Table 4. Tests with a plan experiments on gold 2012/13

| Tests | Content, (k.r), Au (ppm) |      | Recovery (K,J), Au (%) |       |
|-------|--------------------------|------|------------------------|-------|
| T-1   | 1.40                     | 0.26 | 56.1                   | 43.9  |
| T-2   | 1.49                     | 0.29 | 49.8                   | 50.2  |
| O'-1  | 1.56                     | 0.19 | <b>39.91</b>           | 60.09 |
| O'-2  | 1.49                     | 0.25 | <b>58.52</b>           | 41.48 |
| O'-3  | 1.47                     | 0.22 | <b>48.58</b>           | 51.42 |
| O'-4  | 1.49                     | 0.23 | <b>52.03</b>           | 47.97 |
| O'-5  | 1.55                     | 0.24 | <b>52.13</b>           | 47.87 |
| O'-6  | 1.78                     | 0.20 | <b>40.33</b>           | 59.67 |
| O'-7  | 2.55                     | 0.17 | <b>30.86</b>           | 69.14 |
| O'-8  | 2.15                     | 0.19 | <b>39.01</b>           | 60.99 |
| O'-9  | 2.15                     | 0.20 | <b>31.77</b>           | 68.23 |
| O'-10 | 1.95                     | 0.19 | <b>33.82</b>           | 66.18 |

### 3.RESULTS AND DISCUSSION

According to the previous investigations and obtained results from these investigations and tests for the Bucim mine ores, these particular investigation are carried out by means of experiment plans, laboratory investigations etc. These investigations show advanced approach for eventual optimization of the flotation process from useful raw material or chalcopyrite ores with possibility of obtaining the optimal results.

### 4. CONCLUSION

In this paper is shown practical applicative optimization techniques with formatting the model for adequate reagent regime for carried out investigations. Obtained tabular results will show the optimal quantity in reagent regime (collectors), particle size, flotation time for rougher flotation, conditioning time, some addition of special reagents etc.

### REFERENCES

- Mular, A. L., (1980). "Empirical modeling and aptinisation of mineral processes", Mineral Science and Engineering, 4, No 3. Pp 30-42.
- Napier-Munn, T. J., Morrell, S., Morrison, R. D., and Kojovic, T., (1996). "Mineral comminution circuits: their operation and optimization". JKMRCC., pp. 413.
- Plitt, L. R., (December, 1976). "A mathematical model of the hydrocyclone classifier", *CIM Bull.* 69, 114.
- Povarov A. I., (1978). "Hydrocyclones in Mineral Processing", "Nedra". Moskva, Russia.
- Renner, V. G., and Cohen, H. E., (June, 1978). "Measurement and interpretation of size distribution of particles within a hydrocyclone", *Trans. IMM.*, Sec. C, 87,139.
- Rowland C. A., (1986). "Ball Mill Scale-up-Diameter Factors., Advances in Mineral Processing", P. Somasundaran Editor Society of Mining Engineers/AIME, 34, 605.
- Svarovsky, L., (1984). "Hydrocyclones", Holt, Rinehart & Winston Ltd, Eastbourne.
- Wiegel R. L., and Li K. A., (1986). "Random Model for Mineral Liberation by Size Reduction", *Trans. AIME*, 238, 179.
- Wills, B. A. (1988). "Mineral Processing Technology", 4<sup>th</sup> edition
- A.Krstev,(2012), PhD Thesis, 2012 UGD-Stip, Macedonia